

## Silver Aluminium Loaded Fluorosilicone ECF-J

Nolato PPT material reference ECF-J is a fluorosilicone elastomer with a silver / aluminium conductive filler.

Fluorosilicone offers excellent performance over a wide temperature range (-55°C to +160°C) with good resistance to hydrocarbons, chemicals & weathering.

Its resistance to mineral based fluids is limited, but it has good splash resistance to most oils and greases.

### Physical Properties

	Test Methods	Typical Values
Hardness	ASTM D-2240	60±5 IRHD
Specific Gravity	ASTM D-792	2.10±0.1 g/cm <sup>3</sup>
Tensile Strength	ASTM D-412	1.6 MPa
Elongation	ASTM D-412	110% minimum
Compression Set 72 hours @ 100°C	ASTM D-395	30% maximum

### Electrical Properties

Volume Resistivity	Mil-G-83528	0.01Ω/cm maximum
--------------------	-------------	------------------

### Shielding Effectiveness (Mil-G-83528) dB (Mil Std 285)

Frequency	Attenuation
200KHz	79
100MHz	105
500MHz	108
2GHz	102
10GHz	110



Nolato PPT  
 Unit 12, Maldon Trade Park, The Causeway Maldon,  
 Essex, CM9 4LJ, UK  
 Tel: +44 (0) 1376 550525 Fax: +44 (0) 01376 552389  
 Email: [sale.ppt@nolato.com](mailto:sale.ppt@nolato.com) Web: [www.p-p-t.co.uk](http://www.p-p-t.co.uk)

