

Silicone Sheet

Solid Silicone Rubber Sheet - Properties

Hardness	60±5 Shore A
Specific Gravity	1.30 g/cm
Tensile Strength	5.5 MPa
Elongation at Break	450%
Compression Set 70 hours @ 150°C	25%
Temperature Range	-40°C to +200°C

Sponge Silicone Rubber Sheet - Properties

Compression Stress @ 40kPa	90±20
Compression Set 70 hours @ 150°C	6%

Silicone sheet is FDA approved
 Translucent sheet is FDA @ WRC approved
 FDA certificate number 177.2600



Nolato PPT
 Unit 12, Maldon Trade Park, The Causeway Maldon,
 Essex, CM9 4LJ, UK
 Tel: +44 (0) 1376 550525 Fax: +44 (0) 01376 552389
 Email: sale.ppt@nolato.com Web: www.p-p-t.co.uk

